



GLASSWOOL ULTRATEL (48KG/M³)

Introduction

Bradford Ultratel is designed as a high performance internal insulation on HVAC ductwork . It also has many applications as a general insulation product to enhance both thermal and acoustic performance.

Product Description

Bradford Ultratel is manufactured from a rigid engineered glasswool insulation typically with an appropriate facing. The blanket is manufactured by spinning molten glass, containing up to 80% recycled content, into fine wool like fibres.. These are bonded together using a thermosetting resin. The product can be identified by its golden appearance.

Applications

Ultratel is designed to provide high performance internal insulation of heating, air conditioning and cooling ducted systems. Ultratel delivers superior sound absorption and attenuation due to its higher density and rigid properties. Ultratel comes in a range of thicknesses that meet the performance requirements as set out by the Building Code of Australia. Typical HVAC applications include;

- Offices
- High rise
- Hospitals
- Shopping centres etc

Benefits

- High Performance
- Easily handled
- High compressive strength
- Resists damage
- Maximum performance at minimal thickness
- Helps meet the BCA Energy Efficiency provisions
- Easily forms the shape of the duct to be insulated
- Provides both energy and cost savings
- Biosoluble material - safe to use
- Approved for use on site by the Unions

Available Facings

Standard factory applied facings are available. Various grades of Thermofoil as well as black or plain glass tissue, Bradford Ultraphon or Bradford Acoustituff can be adhered to Ultratel to meet the needs of the application. Please contact your nearest Bradford sales office with your requirements.

Thermfoil HD perf is the most common facing for duct lining while Black tissues provides a higher level of acoustic performance and Acoustituff combines acoustic performance with cleanability.

Health and Safety

This product is manufactured to the latest Fibre Bio-Soluble (FBS-1) Glasswool formulation and is not classified as hazardous according to the criteria of the ASCC (formally NOHSC) guidelines. For further information refer MSDS sheet on Bradford website.

SKU Table

Base Blanket Material R-value	Nominal Thickness (mm)	Nominal Length (m)	Nominal Width (mm)	Pieces per Pack	Nominal Coverage per Pack (m ²)
R0.8	25	10	1200	1	12
R0.8	25	10	1500	1	15
R0.8	25	2.4	1200	6	17.3
R1.2	38	10	1200	1	12
R1.2	38	10	1500	1	15
R1.5	50	7.5	1200	1	9
R1.5	50	7.5	1500	1	11.2
R1.5	50	2.4	1200	3	8.6
R2.3	75	2.4	1200	2	5.7

GLASSWOOL ULTRATEL

Physical Properties

Density	kg/m ³	48
Maximum Service Temperature		Glasswool: 350°C; Facing 70°C
Thermal Conductivity	Based on measurements made in accordance with AS2464:5 part 5 and 6	
Fire Hazard Properties	When tested in accordance to AS/NZS 1530.3:1999	<ul style="list-style-type: none"> • Ignitability: 0 • Spread of flame: 0 • Heat Evolved: 0 • Smoke Developed: 0
Compressive Resistance	When tested under comprehensive load, in accordance with BS 2972-1975	
Corrosion Resistance	When tested in accordance with BS 3958.5:1969	pH 7.5-8.0 Incapable to corrode steel
Moisture Absorption	When left in a controlled atmosphere of 50°C and 95% relative humidity for four days	Less than 0.2% by volume
AS4859 Compliance	Complies with AS/NZ4859.1 "Materials for the thermal insulation of buildings"	Complies
Sample Specification		The insulation material shall be Bradford Ultratel Glasswool of thickness () mm faced with (Specify facing). For installation specifications refer to the relevant Application Brochure in the Bradford Insulation Building Literature series.

Sound Absorption

When tested in a reverberation chamber in accordance with AS 1045:1988

Product	Thickness (mm)	Frequency (Hz)							
		125	250	500	1000	2000	4000	5000	NRC
Unfaced	25	0.03	0.24	0.65	0.98	1.07	1.03	1.01	0.73
Perforated Foil Faced	25	0.12	0.31	0.81	1.09	1.09	0.91	0.89	0.77
Unfaced	50	0.34	0.65	1.23	1.11	1.08	1.02	0.98	1.02
Perforated Foil Faced	75	0.69	1.19	1.15	1.09	1.03	0.92	0.9	1.11

Bradford™
for smarter environments

CSR Bradford Insulation

55 Stennett Rd, Ingleburn NSW 2565 Australia.

Telephone (02) 9765 7000 **Facsimile** (02) 9765 7002

www.bradfordinsulation.com.au

CSR Bradford Insulation is a business division of CSR Building Products Limited ABN 55 008 631 356

The contents of this brochure are copyright protected and may not be reproduced in any form without prior written consent of CSR Bradford Insulation. Recommendations and advice regarding the use of the products described in this brochure are to be taken as a guide only, and are given without liability on the part of the company or its employees. We reserve the right to change product specifications without prior notification, please refer to the Bradford website for the latest version of this document. The purchaser should independently determine the suitability of the product for the intended use and application.

GLASSWOOL ULTRATEL – DATA SHEET

CSR